



PAINT TYPE	A multipurpose alkyd primer that can also be used both as primer, primer surfacer, adhesion primer and intermediate coating. Finish: full-matt.
USAGE	FUTURA 3 is intended for priming of surfaces indoors and outdoors, such as furniture, chipboard, fibre board and gypsum board. Also for priming of metal surfaces indoors (also light metal and galvanized surfaces) as well as glass, ceramic tiles, PVC plastic and acid-curing paints indoors. Can also be used for painting ceilings.

TECHNICAL DATA

Solids	About 50 % by volume
Volatile organic compound (VOC)	EU VOC limit value (kat A/i): 500 g/l. The product's VOC: max. 500 g/l.
Practical spreading rate	Applied once onto a smooth surface: 8 - 10 m ² /l. When painting untreated chipboard the spreading rate must be 5 - 6 m ² /l.
Density	abt. 1.4 g/ml
Drying time at +23°C / 50% RH	
- dust free	after 2 hours
- overcoatable	after 6 hours
	The drying process will be slower in cold and/or damp.
Thinner, clean up	TEKNOSOLV 1621 (solvent naphtha) or in spray application TEKNOSOLV 9500
Finish	Full-matt
Colours	White and clear Base 3. Can be tinted with tinting pastes. The colour accuracy is not complete.
Packages (availability varies by country)	White: 0,45 L, 0,9 L, 2,7 L, 9 L Base paint 3: 0,45 L, 0,9 L, 2,7 L, 9 L

SAFETY MARKINGS

See Safety Data Sheet.
NOTE! Because of the danger of self-ignition, any waste from the product, spray mist and soiled rags etc. are to be kept in a fire-proof place in air-tight containers. Immersion in water is also recommended.

PTO

DIRECTION FOR USE**Surface preparation**

Clean the surface from loose matter, dirt and dust.
Wash previously painted surfaces with RENSA SUPER paint cleaner.
Remove rust from the metal surfaces with wire-brush.
Remove loose and poorly adherent paint coats.
Remove all possible latex paints.
Matt down hard or gloss surfaces by sanding and thereafter remove the dust.

Application

Before use stir the paint thoroughly.
For painting wooden surfaces dilute the paint if needed 5 - 10 % with TEKNOSOLV 1621.
Apply by brush, roller or spray.
Suitable airless spray nozzle is 0.013 - 0.015".
When applying by spray, thin the paint 5 - 15% by volume with TEKNOSOLV 9500.

Application conditions

The surface to be painted has to be dry. During the application and drying period the temperature of the ambient air, the surface and the paint shall be above +5°C and the relative air humidity below 80%.

Top coating

The topcoating is applied with FUTURA Top Coats or with Dispersion Paint after the primer has dried for 6 hours.

The information of this data sheet is based on laboratory tests and practical experience. The figures are for guidance only and depend on, for example, colour and gloss. As we have no control over the use and application conditions, we are only responsible for the quality of the product and guarantee that it conforms to our quality control. We accept no liability for any loss or damage resulting from the application of the product contrary to the directions or the intended use. The latest versions of our data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.



EN_635_Tuoteseloste.pdf