

TEKNOCOAT AQUA PRIMER 1868
Water borne pigmented primer
1868-00

TYPE	Water borne pigmented primer with tannin blocking properties.
USE	For tannin rich wood. Only for indoor use.
SPECIAL PROPERTIES	Good filling and good sanding properties. Tannin blocking properties.

TECHNICAL DATA

Density	1.27 kg/l
Solids	51 % by weight 38 % by volume
Volatile organic compound (VOC)	See Safety Data Sheet.
Gloss	Matt.
Storage	See label.
System	TEKNOCOAT AQUA PRIMER 1868-00 is normally sprayed in two layers. Overcoating with water borne topcoats.

DIRECTIONS FOR USE

Application method	Conventional- and automatic spraying.		
Drying time		<u>20 °C</u>	<u>30 °C / 50 min.</u>
	Dry for handling	1 h	After cooling
	Dry for sanding	2 h	After cooling
Thinner	Water		
Cleaning	Water or TEKNOCLEAN 1954-00.		

HEALTH AND SAFETY See Safety Data Sheet.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.
