

TEKNOSEAL 4009-00 is an aqueous and flexible product for the protection of V-joints and corner joints.

TEKNOSEAL 4009-00 is not intended as a filler as it has no structural strength and should not be used to bridge gaps.

TECHNICAL DATA

Binder:	Synthetic binder
Volatile organic compound (VOC):	See Safety Data Sheet.
Colour range:	Colourless

APPLICATION DETAILS

Pre-treatment:	The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %.	
	All softwood and non-durable hardwood for exterior use should either be vacuum impregnated (only softwood) or treated with a wood preservative.	
Application:	Pre-treatment/primer must be thoroughly dry before the product is applied.	
	Is applied by caulk gun in a thin layer. Smooth with damp/moist, but not wet sponge. Possible surplus is removed.	
Application conditions:	The product is delivered ready for use. Contraction of volume approx. 25 %.	
	Optimum temperature for products and surroundings: Do not use below temperatures of 15 °C	18-25 °C
	Optimum relative air humidity:	Approx. 50 %
System treatment:	Primed parts must always be protected with a topcoat treatment before they are exposed to the influence of the weather.	
Drying times:	Determined at 23 °C and 50 % RH:	
	Dry to handle:	1 mm thickness 2 hours 1.5 mm thickness 4 hours
	Excessive application amounts and / or high humidity and / or low temperatures will significantly extend drying times.	
Cleaning:	The equipment is cleaned with water.	

HEALTH AND SAFETY See Safety Data Sheet.

ADDITIONAL INFORMATION

Pack size:	320 ml cartridge
Storage:	The product must be stored at temperatures above 5 °C. Shelf life in unopened containers: See "Best before date" on the label. Keep containers tightly closed after use.