

## Guide To Quantities of Rustoleum Coatings Required For 10 & 15 Year Warranty On Roofing and Vertical Cladding Systems

### Noxyde Warranty

For all warranty systems you will require the use of AMW Wash to remove algae and any other green growth, followed by a clean and degrease with Rustoleum ND14. These quantities will be determined by condition of the substrate.

To qualify for the warranty, a Plastisal roof will need to be a minimum area 500m<sup>2</sup>. A site visit will be required arranged by Promain UK Limited and a work card will need to be completed before work commences, allow a minimum of 3 weeks before work commences for this to be arranged.

Allow approximately 30% extra material for stripe coat, edge lap repair and including additional area for corrugated profile.

#### Materials Required For 10 Year Noxyde Warranty

Roofs            2 coats at 400 gms per m<sup>2</sup>  
Verticals        2 coats at 300 gms per m<sup>2</sup>

#### Materials Required For 15 Year Noxyde Warranty

Roofs            2 coats at 500 gms per m<sup>2</sup>  
Verticals        2 coats at 400 gms per m<sup>2</sup>

### Noxyde & Metal Cladding Topcoat Warranty

#### Materials Required For 10 Year Decorative Warranty for Vertical Cladding

1 coats at 400 gms per m<sup>2</sup> Noxyde  
1 coat of Metal Cladding Topcoat at 8m<sup>2</sup> per litre

### Pegarust Warranty

#### Materials Required For 10 Year Pegarust Warranty

Roofs            2 coats at 2.9 m<sup>2</sup> per litre per coat  
Verticals        2 coats at 2.9 m<sup>2</sup> per litre per coat

All of these systems can be overcoated with Rustoleum Metal Cladding Topcoat to provide in excess of 30,000 colours.

