

## TECHNICAL DATA SHEET

TDS: CVW138T

### CLEAR GLAZE FOR FLOORS

116/W138/T

#### DESCRIPTION:

Used on wooden and concrete floors to provide a quick drying and protective clear coat. A water based product.

#### RECOMMENDED USE:

Ideal for use where fast drying and no solvent smell is important.

#### AVAILABILITY:

1 litre, 2.5 litre, 5 litre

#### FINISH:

Off Gloss

#### COLOUR:

Clear

#### TYPICAL S.G. (SPECIFIC GRAVITY):

1.03 @ 20 °C

#### VOLUME SOLIDS:

38%

#### WET FILM THICKNESS W.F.T

90 microns

#### DRY FILM THICKNESS D.F.T

25 to 30 microns

#### EXPECTED SPREADING RATE:

11 sq.m / litre  
@ 30 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

#### TYPICAL VISCOSITY:

2.5 Poise @ 25 °C

#### FLASH POINT:

Non-flammable

#### DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 1.5 hours @ 20 °C

Hard dry: 6 hours @ 20 °C

Full hardness: 3 to 5 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

#### MINIMUM OVERCOATING TIME:

6 hours

#### APPLICATION SPECIAL CONDITIONS:

#### VOC CONTENT:

Max 87 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

#### APPLICATION DETAILS:

Application Do not apply below 7 °C. restrictions

Method: Brush or Roller

Thinner Clean Water  
(Max vol): (5%)

Nozzle size: N/A

Nozzle N/A  
pressure:

Cleaning Water  
solvent:

Recoat 6 hours  
interval:

#### SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants. New wood should be sanded prior to coating to ensure an adequate "key" is produced. Existing painted surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose, flaking material and treat bare areas as

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR

Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)

[www.coo-var.co.uk](http://www.coo-var.co.uk)

**CLEAR GLAZE FOR FLOORS****116/W138/T**

---

new substrate then prepare accordingly.

**MIXING INSTRUCTIONS:**

Mix well before use.

**APPLICATION CONDITIONS:**

As dictated by normal good painting practice.  
Do not apply if the temperature is likely to drop below 7 °C during application or during the drying process.

**PRECEDING COAT:**

Apply direct to prepared wood and concrete.

**SUBSEQUENT COAT:**

Coo-Var Clear Glaze for Floors

**REMARKS:**

Do not paint when temperature will be at or below 7 °C during the painting and drying process.

**HEALTH AND SAFETY:**

See safety data sheet - SDS 10626

**ISSUED:**

10 December 2018

**REVISION:**

1

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

**For further advice contact Coo-Var Technical Services on +44(0)1482 328053**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

---

Ellenshaw Works  
Lockwood Street, Hull HU2 0HN  
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR  
Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)  
[www.coo-var.co.uk](http://www.coo-var.co.uk)