



PRODUCT DATA SHEET

Centrecoat

Adhesion Promoter

- Quick Drying
- Can be overcoated with 1K or 2K finishes
- Aids adhesion on difficult to prepare substrates
- No waste ready for use

Details

A single pack adhesion promoter to improve the adhesion of a wide range of solvent based surface coatings over a wide range low surface energy plastics such as Thermoplastic olefins (TPO), Thermoplastic urethane, (TPU), Acrylonitrile Butadiene Styrene, (ABS), and release agent free Polypropylene. Suitable for both flexible and rigid substrates and sheet moulded composites (SMC).

May also be used to promote adhesion to a wide range of difficult to adhere to substrates including power floated concrete, engineering, bricks, ceramics, aluminium, galvanising, as well as promoting intercoat adhesion between paint coatings

Colour : Transparent with a pale straw tint when wet

Active Solids Content : 5% by weight.

Film Thickness : A film thickness of 5-10 microns is the optimal required dry film thickness required. Take care to avoid over application

Theoretical Coverage : In order to achieve the required coverage rate the product should be applied at 12.5 square meters per litre.

Method of Application

Preferred method of application is by conventional air assisted spray. If applying by airless spray or air assisted airless spray a tip size of 9-11 thou will be required, care must be taken to avoid over application. If applying by brush or roller use the theoretical coverage rate to ensure over application does not occur.

Drying Time :

Touch Dry 3-5 minutes.

Dry for over coating 10-15 mins.

Drying times are quoted at 20°C and will vary with actual conditions such as air movement, temperature and humidity.