

**RUST-OLEUM**  
INDUSTRIAL



## **HARD HAT® GALVA ZINC**

# **Cathodic protection of bare and galvanised steel**

- Cathodic protection of bare and galvanised steel
- 90% pure zinc in dry paint film
- Resists 500 hours of salt spray testing (DIN 50021 SS)
- To recoat within one hour, brush version after 4 hours
- To recoat with HARD HAT® metallic sprays

**KNOW-HOW TO PROTECT™**

**WWW.RUST-OLEUM.EU**

# HARD HAT® GALVA ZINC

## DESCRIPTION

Hard Hat® Aerosol Zinc Spray Cold Galvanising Compound 2185 is a fast drying zinc rich primer based on an epoxy ester resin. The product contains pure zinc as pigment and provides cathodic protection.

## RECOMMENDED USE

RUST-OLEUM Zinc Spray 2185 should be used on new, bare steel or galvanised steel surfaces. RUST-OLEUM Zinc Spray 2185 is intended to be applied on small areas or for touch-up. RUST-OLEUM Zinc Spray 2185 can be recoated with non-saponifiable coatings. RUST-OLEUM Zinc Spray 2185 should be used as a primer or as a single coat in light industrial exposures, corrosive environments and high humidity areas.

## TECHNICAL DATA

Gloss Level: Matt  
Propellant: Dimethyl ether  
Heat Resistance: 450°C (dry heat)

## DRYING TIMES AT 20°C/RH 50%

Touch dry: 10 minutes  
Dry to handle: 30 minutes  
Dry to recoat: Within 1 hour or after 48 hours  
Fully cured: 7 days

## RECOMMENDED WET FILM THICKNESS

100 µm

## RECOMMENDED DRY FILM THICKNESS

35 µm

## THEORETICAL CONSUMPTION

1,4 m<sup>2</sup> per spray can at 35 µm dry

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. The surface must be clean and dry during application.

## APPLICATION CONDITIONS

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply a full, wet coat to achieve a close, dense coating film, avoid dry spray. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

## SAFETY DATA

VOC level: 630 g/l  
Remarks regarding safety: Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 24/04/2018

**Available colours & pack sizes :** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer :** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)