

## TECHNICAL DATA SHEET

TDS: CVG119D

347/G119

### PRIMALL

#### DESCRIPTION:

Coo-Var Primall is a multi-surface primer / sealer made with low odour solvents. Gives excellent coverage to a multitude of stains, helping to prevent it bleeding through the finishing coat.

#### RECOMMENDED USE:

Coo-Var Primall is a coating which offers excellent stain blocking and alkali resisting properties across substrates such as tiles, wood, metal (including galvanised), plaster, existing paint, masonry and most plastics. Suitable for interior or exterior use.

#### AVAILABILITY:

0.5 litre, 1 litre, 2.5 litre, 5 litre

#### FINISH:

Matt

#### COLOUR:

White

#### TYPICAL S.G. (SPECIFIC GRAVITY):

1.10 @ 20 °C

#### VOLUME SOLIDS:

36%

#### WET FILM THICKNESS W.F.T

100 microns

#### DRY FILM THICKNESS D.F.T

35 to 40 microns

#### EXPECTED SPREADING RATE:

10 sq.m / litre

@ 40 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

#### TYPICAL VISCOSITY:

4.0 Poise - C&P @ 25 °C

#### FLASH POINT:

Above 32 °C (closed cup)

#### DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 30 mins @ 20 °C

Hard dry: 4 hours @ 20 °C

Full hardness: 3 to 5 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

#### MINIMUM OVERCOATING TIME:

Minimum 4 to 6 hours

#### APPLICATION SPECIAL CONDITIONS:

N/A

#### VOC CONTENT:

max 499 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

#### APPLICATION DETAILS:

Application N/A  
restrictions

Method: Brush or Roller

Thinner Do not thin  
(Max vol):

Nozzle size: 0.013"

Nozzle N/A  
pressure:

Cleaning Thinner 18 or  
solvent: LO white spirit

Recoat Minimum 4 to 6  
interval: hours

#### SURFACE PREPARATION:

**For further advice contact Coo-Var Technical Services on +44(0)1482 328053**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR

Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)

[www.coo-var.co.uk](http://www.coo-var.co.uk)

**PRIMALL****347/G119**

---

All surfaces should be clean, dry, sound and free from oil and dirt. Wire brush or sand surface to remove any loose / flaking material and rust.

**MIXING INSTRUCTIONS:**

Mix well before use.

**APPLICATION CONDITIONS:**

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

**PRECEDING COAT:**

N/A

**SUBSEQUENT COAT:**

Any suitable topcoat.

**REMARKS:****HEALTH AND SAFETY:**

See safety data sheet - SDS 11327

**ISSUED:**

18 April 2013

**REVISION:**

1

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

**For further advice contact Coo-Var Technical Services on +44(0)1482 328053**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

---

Ellenshaw Works  
Lockwood Street, Hull HU2 0HN  
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR  
Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)  
[www.coo-var.co.uk](http://www.coo-var.co.uk)