3105

a five page issue

January 2010 revision of May 2008

Application areas: wet and dry accommodation spaces, service spaces.

Contains the following specifications:

Specification 1: multi-purpose epoxy system with an alkyd finish Specification 2: multi-purpose epoxy system with an alkyd finish

Specification 3: recoatable polyurethane/epoxy system

Specification 4: alkyd system

Specification 5: waterborne acrylic coating system

Specification 6: emulsion paint system

#### **GENERAL ASPECTS**

Paint systems for wet accommodation spaces, such as bath rooms, showers, galleys and toilets must be corrosion inhibiting, water, soap and scratch-resistant, easy to clean and non yellowing. For reasons of hygiene they should be light coloured.

Paint systems for dry accommodation spaces among which engine room, provision store, cabins, hospital, etc. should have long lasting adhesion to the various substrates, be easily recoatable and usually decorative.

#### **VENTILATION**

Adequate ventilation must be maintained during application and curing (please refer to sheet 1433 and 1434)

SPECIFICATION 1	multi-purpose epoxy system with an alkyd finish system is certified for low flame spread, see sheet 1883B	
pretreatment	steel without mill scale; blast cleaned to ISO-Sa2½, blasting profile 40 - 70 µm or power tool cleaned to ISO-St3 steel with approved shop primer; sweep blasted to SPSS-Ss or power tool cleaned to SPSS-Pt2	
paint system	SigmaPrime 700 Sigmarine 48	75 μm 35 μm
maintenance	should preferably be carried out to this specification	





3105

January 2010

SPECIFICATION 2	multi-purpose epoxy system with an alkyd finish system is certified for low flame spread, see sheet 1883B	
pretreatment	steel without mill scale; blast cleaned to ISO-Sa2½, blasting profile 40 - 70 µm or power tool cleaned to ISO-St3 steel with approved shop primer; sweep blasted to SPSS-Ss or power tool cleaned to SPSS-Pt2	
paint system	SigmaPrime 200 Sigmarine 48	75 μm 35 μm
maintenance	should preferably be carried out to this specification	

SPECIFICATION 3	recoatable polyurethane/epoxy system with excellent hygienic profor wet and dry accommodation and service spaces system is certified for low flame spread, see sheet 1883B	perties
pretreatment	steel without mill scale; blast cleaned to ISO-Sa2½, blasting profit 40 - 70 µm or power tool cleaned to ISO-St3 steel with approved shop primer; sweep blasted to SPSS-Ss or potool cleaned to SPSS-Pt2 galvanised steel and aluminium; degreasing and removal of salts means of mechanical cleaning and rinsing e.g. by brushing with ribrushes and use of abundant clean fresh water, followed by rough up surface must be allowed to dry completely polyester and other plastics (to be specified and checked); degreatived of contaminants by means of mechanical cleaning wood, has board, chip board; to be sanded before and after application of the primer coat	by hylon nening ased and ard
paint system	SigmaCover 280 SigmaCover 456 SigmaDur 550	50 μm 75 μm 50 μm
maintenance	should preferably be carried out to this specification	





3105

January 2010

SPECIFICATION 4	alkyd system for dry accommodation spaces when fully cured and permanently exposed to water system is certified for low flame spread, see sheet 1883B	not
pretreatment	steel without mill scale; power tool cleaned to ISO-St3 steel with approved shop primer; power tool cleaned to SPSS-Pt2 wood, hard board, chip board; to be sanded before and after applic the first primer coat	ation of
paint system	Sigmarine 28 Sigmarine 48	75 μm 35 μm
notes	<ul> <li>for wood, hard board and chip board Sigmarine 28 can be replaced by Sigmarine 40 if a very smooth surface is required, a knifing filler should be applied after application of the (thinned) primer</li> <li>one coat of Sigmarine 28 can be replaced by 2 coats of Sigmarine 24 at a dft of 35 µm each</li> </ul>	
maintenance	should preferably be carried out to this specification	

SPECIFICATION 5	water borne acrylic coating system for dry accommodation spaces system is certified for low flame spread, see sheet 1883B	
pretreatment	steel without mill scale; blast cleaned to ISO-Sa2½, blasting profile 40 - 70 µm or power tool cleaned to ISO-St3 steel with approved shop primer; sweep blasted to SPSS-Ss or power tool cleaned to SPSS-Pt2	
paint system	Sigma AquaCover 25 Sigma AquaCover 45	75 μm 50 μm
maintenance	should preferably be carried out to this specification	





3105

January 2010

SPECIFICATION 6	emulsion paint system for soft board ceilings, plastered pipelines, fibre cement plates and insulating materials with good resistance to wet scrubbing	
	system is certified for low flame spread, see sheet 1883B	
pretreatment	all substrates; removal of contaminants highly absorbent surfaces, to be impregnated with a strong diluted extra coat	
paint system	· ·	40 μm 40 μm
maintenance	should preferably be carried out to this specification	





3105

January 2010

#### **REFERENCES**

Sigma AquaCover 25	see product data sheet 7150
Sigma AquaCover 45	see product data sheet 7250
SigmaCover 280	see product data sheet 7417
SigmaCover 456	see product data sheet 7466
SigmaDur 550	see product data sheet 7537
SigmaPrime 200	see product data sheet 7416
SigmaPrime 700	see product data sheet 7930
Sigmarine 24	see product data sheet 7135
Sigmarine 28	see product data sheet 7117
Sigmarine 40	see product data sheet 7213
Sigmarine 49	see product data sheet 7240
Sigmarine 48	see product data sheet 7238
Sigmatex	see product data sheet 8215
Safe working in confined spaces	see information sheet 1433
Directives for ventilation practice	see information sheet 1434
Cleaning of steel and removal of rust	see information sheet 1490
Certificates for low-flame spread	see information sheet 1883B
prefabrication primers	see system sheet 3015

Limitation of Liability - The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the Sigma Coatings products made by PPG Protective & Marine Coatings, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. The products and information are designed for users having the requisite knowledge and industrial skills and it is the end-user's responsibility to determine the suitability of the product for its intended use.

PPG Protective & Marine Coatings has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. PPG Protective & Marine Coatings does therefore not accept any liability arising from loss, injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product.



