

## VANDALENE ANTI-CLIMB PAINT

200/C264/ -

### DESCRIPTION:

A thick single pack non-drying product of sticky nature, providing a slippery surface. Contains a hidden identifier.

### RECOMMENDED USE:

For use on window ledges, down pipes, walls, gutters, anywhere which may be used as a grip point to gain unauthorised access.

### AVAILABILITY:

0.8kg, 2kg, 4kg

### FINISH:

Semi matt

### COLOUR:

Black, Red, Grey, Green

### TYPICAL S.G. (SPECIFIC GRAVITY):

1.0

### VOLUME SOLIDS:

84 - 90%

### WET FILM THICKNESS W.F.T

0.5 mm

### DRY FILM THICKNESS D.F.T

0.5 mm

### EXPECTED SPREADING RATE:

1 - 2 sq.m / kilo

0.5 mm d.f.t. (based on application by brush or mitt)

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

### TYPICAL VISCOSITY

Grease like

### FLASH POINT:

above 32C

### DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: N/A

Hard dry: N/A

Full hardness: N/A

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

### MINIMUM OVERCOATING TIME:

Not required

### APPLICATION SPECIAL CONDITIONS:

Use at heights over 1.8 metres away from daily legitimate use.

### VOC CONTENT:

144 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

### APPLICATION DETAILS:

Application N/A  
restrictions

Method Brush or mitt

Thinner Do not thin  
(Max vol):

Nozzle size: N/A

Nozzle N/A  
pressure:

Cleaning White spirit or  
solvent: turps sub.

Recoat Not required  
interval:

### SURFACE PREPARATION:

Ensure all surfaces are clean, dry and free from grease, oil and any other contaminates. Seal

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

**VANDALENE ANTI-CLIMB PAINT****200/C264/ -**

---

porous surfaces first. Roughen smooth surfaces using coarse abrasive paper or by wire brushing. Metal should be suitably prepared and primed prior to application.

**MIXING INSTRUCTIONS:**

N/A

**APPLICATION CONDITIONS:**

As dictated by normal good painting practice. In confined spaces provide adequate ventilation during application and drying.

**PRECEDING COAT:**

Coo-Var Acrylic Primer Sealer on masonry and wood and other porous surfaces, Coo-Var All Metals Primer if applying to metals.

**SUBSEQUENT COAT:**

Not required

**REMARKS:**

Notification signs should be used. Use in areas where temperatures do not normally exceed 30C.

**HEALTH AND SAFETY:**

See safety data sheet - SDS 10429

**ISSUED:**

20 May 2009

**REVISION:**

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, since the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department.

**For further advice contact Coo-Var Technical Services on +44(0)1482 328053**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

---

Ellenshaw Works  
Lockwood Street, Hull HU2 0HN  
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-var  
Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)  
[www.coo-var.co.uk](http://www.coo-var.co.uk)