



## TECHNICAL DATA SHEET

# KEIM AIRLESS TECHNIQUE

## 1. GENERAL INFORMATION

There are two fundamentally different airless pumping systems:

### Diaphragm pumps:

Pumping pressure generated by pulsating membrane

### Piston pumps:

Pumping pressure generated by moving pistons (as in a combustion engine)

While the diaphragm pump is known as being low in wear and maintenance, the piston pump is characterised by its high performance. It is generally extremely important to adhere to the minimum hose length stated by the manufacturer, as said length also serves as pulsation compensation.

## 2. DESCRIPTION OF TERMS

### Inch:

American length unit corresponding to 2.54 cm, used in airless technology as nozzle size statement (diameter of nozzle hole).

### Mesh:

Mesh width for screens, dimensions for particle or grain size – the following applies:  
the smaller the mesh size, the larger the screen.

### Back pressure:

The entire system (airless device, high pressure hose, spray gun) is subject to the pressure set at the pressure regulator when the spray gun has not been detached.

### Operating pressure:

As soon as the spray gun is activated, as low operating pressure (spraying pressure) is set at the pressure regulator.

### High pressure filter:

Filter insert in a filter housing, in the direct pressure range of the airless device, i.e. the filter is always under pressure when the machine is running.

### Gun filter:

Filter insert in the handle of the spray gun.

### Adjustable nozzle:

The nozzle diameter can be enlarged or reduced (optimised) by means of an adjustable pin located in the nozzle hole.

### Nozzle designation:

If the nozzle has a marking e.g. "525" or if such a marking is contained in the manufacturer's documentation, this means that the nozzles have a spraying angle of 50° (5) and a nozzle hole of 0.025 inch (25) (corresponds with 0.64mm).

## 3. NOTES

Attention must generally be paid that a nozzle with a wide spraying angle i.e. with 50° or 60° is used for optically flawless coating.

A spraying angle as narrow as possible (30° or 40°) is to be used for application methods in which the applied paints is rolled on using a paint roller.

Always test your device with water first, as it is frequently possible that the ball valves in the suction tube are jammed.

Lubricate the pump regularly with release oil (piston pump). Protect all system components coming into direct contact with paint material by using a cloth soaked in release oil to wipe down the components. Clean the system meticulously after airless spraying to rule out interruptions during the next use.

Use at least one filter in the system (usually high pressure filters) to avoid nozzle clogging and the resulting damage to the painting result.

If the device is not in use for a long period of time, it is advisable to wipe all moving pump components (ball valves) with oil (e.g.: salad oil), so that they do not seize upon the next use. Known device manufacturers now offer a sealing and valve fluid that keeps all pump components movable.



**SPRAY PARAMETERS FOR KEIM PRODUCTS**

KEIM product	Filter	Nozzle	Back pressure	Temperature
AquaRoyal-Color*	30mesh Pi	≥ 435	> 70 bar	
Blockweiß*	30mesh Pi	≥ 525	> 170 bar	
Biosil	30mesh Pi	≥ 423	120 bar	40°C
Concretal-Base	50mesh Pi	≥ 512	170 bar	
Concretal-C*	30mesh Pi	≥ 423	110 bar	
Concretal-Lasur	50mesh Pi	≥ 512	> 170 bar	
Concretal-W*	30mesh Pi	≥ 435	95 bar	
Concretal-W-Grob*	without filter	> 443	> 110 bar	
Design-Lasur**	100mesh Pi	≥ 512	> 170 bar	
Dolomitspachtel*	without filter	≥ 443	> 110 bar	
Ecosil-ME	50mesh Pi	≥ 423	120 bar	40°C
Granital*	30mesh Pi	≥ 435	70 bar	
Granital-Grob*	without filter	≥ 443	> 100 bar	
Grundierweiß	50mesh Pi	≥ 421	90 bar	
Intact*	without filter	≥ 443	> 100 bar	35°C
Innostar	50mesh Pi	≥ 421	80 bar	40°C
Innotop	50mesh Pi	≥ 423	100 bar	40°C
Innotop-Grob*	without filter	≥ 443	> 100 bar	40°C
Lignosil-Base/W	50mesh Pi	≥ 512	> 150 bar	
Lignosil-Color	50mesh Pi	≥ 417	100 bar	
Lignosil-Verano	50mesh Pi	≥ 417	80 bar	
LS-Pro*	without filter	≥ 525	> 150 bar	
Mycal-Top	50mesh Pi	≥ 423	120 bar	40°C
Novosil*	30mesh Pi	≥ 435	75 bar	
Novosil-Grob*	without filter	≥ 443	> 100 bar	
Optil	30mesh Pi	≥ 423	110 bar	
Optil-Grob*	without filter	≥ 443	> 100 bar	
Quarzil*	30mesh Pi	≥ 435	70 bar	35°C
Quarzil-Grob*	without filter	≥ 443	> 100 bar	
Quarzil hist.*	30mesh Pi	≥ 435	> 90 bar	
Quarzil hist. Grob*	without filter	≥ 443	> 100 bar	
Romanit-Farbe*	30mesh Pi	≥ 425	> 90 bar	
Soldalit*	30mesh Pi	≥ 435	> 85 bar	
Unikristalat	30mesh Pi	> 435	> 85 bar	
Veramin	30mesh Pi	≥ 435	> 90 bar	35°C

The values stated in the table refer to a certain device type and are only standard values. Note: Higher spray angles may require larger nozzle diameters. Pi=Gun filter. The respective pressure values refer to the concrete nozzle sizes stated in the table.

\*) Do not use diaphragm pumps    \*\*) Metallic colour shades with 50 mesh filter

