

## PRODUCT DATA

## DACFILL MESH

### DESCRIPTION

Polyester fibres woven in hexagonal meshes.

### RECOMMENDED USES

Reinforcement of the first coat of Dacfill for the system Dacfill-Waterproofing.

### TECHNICAL DATA (according to the data given by the manufacturer)

Composition	:	100% polyester fibres
Quality	:	Flexible
Weight	:	48 - 52 g/m <sup>2</sup>
Thickness	:	0,28 - 0,29 mm
Traction force in N/5 cm	By warp	: ± 140
	By weft	: ± 95
GRAB elongation in %	By warp	: ± 29
	By weft	: ± 260
Resistance to	UV	: Good - behind glass 7 to 10 years
	Temperature	: Good
	Acids	: In 50% of sulphuric acid - room temperature - 6 months.
	Alkali	: Good - only the surface of the fibres will be attacked at room temperature.
Thermal retraction at 40°C	By warp	: ± 3
	By weft	: ± 1,7%
Dimensions	Widths	: 20 cm, 60 cm en 100 cm
	Roll length	: 100 m
Tolerances	Width	: None
	Length	: - 0 m + 1 m

**Rust-Oleum Netherlands B.V.**  
Braak 1, 4704 RJ  
P.O. Box 138, 4700 AC  
Roosendaal, The Netherlands  
T +31 (0)165 593 636  
F +31 (0)165 593 600  
[info.nl@ro-m.com](mailto:info.nl@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
B - 3545 Zelem  
Halen, Belgium  
T +32 (0)13 460 200  
F +32 (0)13 460 201  
[info.be@ro-m.com](mailto:info.be@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

**Rust-Oleum France S.A.S**  
11, Rue Jules Verne, B.P. 60039  
95322 St-Leu-la-Forêt Cedex  
France  
T +33 (0)130 400 044  
F +33 (0)130 409 980  
[info.fr@ro-m.com](mailto:info.fr@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

**Rust-Oleum UK Ltd.**  
Unit 6, Spitfire Close  
Coventry Business Park  
Coventry, CV5 6UR  
United Kingdom  
T +44 (0)2476 717 329  
F +44 (0)2476 718 930  
[info.uk@ro-m.com](mailto:info.uk@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

**Rust-Oleum Mathys Italia s.r.l.**  
Largo Donegani 2  
20121 Milano, Italia  
T +39 335 10 93 482  
[info.it@ro-m.com](mailto:info.it@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)