

PRODUCT DATA**HARD HAT® AEROSOLS GALVA-PLUS 2120****DESCRIPTION**

RUST-OLEUM® Hard Hat Aerosol Galva-Plus Silver 2120 is a fast drying zinc/aluminium coating based on an epoxy ester resin. The product contains pure zinc and aluminium as pigment.

RECOMMENDED USES

RUST-OLEUM Galva-Plus Silver 2120 should be used for touch-up of galvanised steel surfaces.

RUST-OLEUM Galva-Plus Silver 2120 is intended to be applied on small areas or for touch-up.

RUST-OLEUM Galva-Plus Silver 2120 should be used as a single coat in light industrial exposures and corrosive environments.

TECHNICAL DATA

Appearance:	Flat
Colour:	Silver metallic
Propellant:	Dimethyl ether
Recommended film thickness:	25 µm dry, equals 100 µm wet
VOC-content:	655 g/l

Drying times	20°C/50% r.v.
To touch:	15 minutes
To handle:	60 minutes
To recoat:	Within 2 hours or after 48 hours
Full hardness	7 days
Heat resistance:	150°C (dry heat)

Coverage

Theoretical: 1.7 m² per spray can at 25 µm dry

Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. The surface must be clean and dry during application.

DIRECTION FOR USE

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply a full, wet coat to achieve a close, dense coating film, avoid dry spray. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

APPLICATION CONDITIONS

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Rust-Oleum Netherlands B.V.
Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info@rust-oleum.eu
www.rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S
11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)1 30 40 00 44
F +33 (0)1 30 40 99 80
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.
Rotterdam House
116 Quayside
Newcastle
NE1 3DY
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info@rust-oleum.eu
www.rust-oleum.eu