

<b>Factors</b>	<b>Zinga</b>	<b>Galvafruid</b>
Zinc content by weight	96%	90 -92%
Shelf life in the container	Unlimited	One year
Pot life	Unlimited	24 hours
Drying time to re-coat with itself	< 1 hour	24 hours
Drying time to handle	< 1 hour	24 hours
Drying time to overcoat with epoxy	24 hours	3 days
Minimum application temperature	-15°C	5°C
Application onto damp substrate	Yes	No
Maximum working temperature	150°C	116°C
Minimum working temperature	-40°C	0°C
Working ph range	atmospheric : ph5.5 – ph12.5 immersion: ph5.5 – ph 9.0	atmospheric : ph5.5 – ph9.0 immersion: ph5.5 – ph9.0
Certified for use with potable water	Yes	No
Certified as non-flammable	Yes	No
Certified by BBA	Yes	No
Certified by NATO	Yes	No
Certified by MoD	Yes	No
Certified to NORSOK M501-7	Yes	No