

Specification For The Coating Of Metal Gutters

1. Rake out all Gutter Joints of old friable mastic or rubber seals ensure gutter is clean and dry.
2. Apply Zinc Phosphate primer at a coverage of 7 - 8m²/ltr and allow to dry 1-2 hours under normal conditions.
3. Gun in Exterior grade Flexible filler to all joints allow to dry.
4. Apply Acrypol Waterproof Roof coating to all joints and into the wet Acrypol incorporate 15cm wide Scrim.
5. Allow to dry overnight.
6. Apply first coat of Acrypol + Waterproof roof coating at a coverage of 1kg/m².
7. Allow to dry.
8. Apply a second coat of Acrypol + Solar white Waterproof Roof Coating at a coverage of 1kg/m².
9. Asphalt and Concrete Gutters different sealer As8000 at a coverage of 6-8m²/ltr