

# Centrecoat™ Progrip



Technical Data Sheet

## PRODUCT DESCRIPTION

Centrecoat Progrip Methyl Methacrylate (MMA) cold plastic lining system. A proven system to last, extremely durable and matches the demands of today's increased traffic volumes. Utilises traditional marking tools and skills and available in a range of colours. Will last longer than any other proprietary markings and is applied without any hot works involved.

## PROPERTIES

Rapid cure at low temperatures.  
BBA & HAPAS approved.  
Very durable, slip resistant coating.  
Excellent bond to concrete, steel and asphalt.  
Can be trafficked within one hour.  
Easy to apply.  
Excellent anti-ageing properties and U.V resistant.  
Very good abrasion and chemical resistance.  
Good low temperature flexibility.  
Available in a range of colours.

## RECOMMENDED APPLICATION METHODS

Apply by brush, 4 mm serrated rubber squeegee or roller.  
Ensure that surface to be coated is dry and free from oil, dust, road salts and other contaminants before application is commenced.  
Do not apply at temperatures below 5°C.  
Mechanically mix both components together thoroughly before use.

## TECHNICAL

Appearance:	Viscous liquid
Colour:	Varying
Odour:	Characteristic
Solubility:	Slightly soluble in water. Miscible with: organic solvents
Boiling point:	~ 100°C @ 760 mm hg
Flash point:	~ 17°C cc (closed cup)
Auto ignition temperature:	~ 430°C

## COVERAGE

Theoretical: 1.7 kg/ metre squared.

## AVERAGE DRYING TIMES

Cure time:	40 minutes
Working life:	12 minutes

## PACKAGING

Supplied in:	2 and 8 kg containers.
Shelf life:	6 months.
Store between:	5 and 25°C.