

PRODUCT DATA

PEGACRYL SATIN

DESCRIPTION

Waterborne satin gloss acrylic paint.

MAIN PROPERTIES

Weather resistance better than most synthetic enamels - good flow - good filling power - high covering capacity.

RECOMMENDED USES

Woodwork, both inside and outside. As topcoat on Noxyde.

TECHNICAL DATA

Appearance:	Satin gloss (gloss 60°: ±30%)
Colour:	White + colour chart
Density:	1.25 - 1.32 g/cm ³
Solids Content:	In volume: 31 - 34% In weight: 47 - 51%
Recommended film thickness:	Wet film: 100 micron (cons.: 10 m ² /l) Dry film: 35 micron (cons.: 10 m ² /l)
Flashpoint:	Not flammable
VOC-content:	128 g/l max.
Ready-for-use mixture:	128 g/l max.
Category:	A/d
EU Limit values:	150 g/l (2007) / 130 g/l (2010)

Drying times	20°C/50% r.h.
To touch:	1 hours (10 m ² /l)
To handle:	5 hours (10 m ² /l)
To recoat:	24 hours
Full hardness	± 2 days

Coverage

Theoretical:	9 -12 m ² /l
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Painted substrates: apply directly on old sound paints; glossy paints will be roughed up slightly.

Untreated substrates: on woodwork, apply a coat of Fassiprim Aqua.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush:	Do not dilute.
Roller:	Do not dilute.
Air-atomised spray:	Dilute with water.
Airless spray:	Nozzle: 018 / Pressure: 180 bars / If necessary, dilute with some water.
Cleanup:	Water.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com

PRODUCT DATA

PEGACRYL SATIN

APPLICATION CONDITIONS

> 10°C; < 80% H.R.

REMARKS

Apply Pegacryl Satin by preference by airless or brush.

Do not apply in full sun or too hot conditions, to avoid a decreased flow.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com