

## Sikagard®-680 S

### Protective coating for concrete

#### Product Description

Sikagard®-680 S is a one part solvent containing coating, based on methacrylic resins resistant to weathering, alkalis and ageing. It is available in clear and coloured grades for use on mineral substrates including concrete and other cementitious surfaces

Sikagard®-680 S protects concrete against aggressive atmospheric influences and promotes a self-cleaning effect on the treated surfaces. It does not adversely influence the characteristic texture of the concrete.

Sikagard®-680 S complies with the requirements of EN 1504-2 as protective coating.

#### Uses

Sikagard®-680 S is used for protection and enhancement of concrete and other cementitious materials on building and infrastructures elements

Sikagard®-680 S clear glaze is a colourless material drying to a glossy coat, suitable as refresher and protective coating for exposed aggregate concrete

Sikagard®-680 S top coat is a top coating, drying to a mat finish, available in a large number of decorative standard and almost unlimited special colour shades.

- Suitable for protection against ingress (Principle 1, method 1.3 of EN 1504-9),
- Suitable for moisture control (Principle 2, method 2.3 of EN 1504-9)
- Suitable for increasing the resistivity (Principle 8, method 8.3 of EN 1504-9)

#### Characteristics / Advantages

- Sikagard®-680 S provides excellent weather resistance and is based on a methacrylic resin with fast evaporating solvents
- Due to its quick drying properties, the coating is rain resistant within a short time
- Almost no change in the texture characteristics of the concrete surface
- Sikagard®-680 S protects the concrete against aggressive atmospheric influences, which can penetrate into the concrete in the form of salts or gases
- Very high diffusion resistance against carbon dioxide and, therefore reduces considerably the rate and depth of carbonation of the concrete
- Water vapour permeability is not adversely affected
- Dirt pick up is reduced and the concrete is no longer discoloured by rain
- Suitable for sealing of green concrete in civil engineering works

#### Tests

##### Approval / Standards

Report Nr.:A 2216/C1 dated 22. 11. 1990, IBAC Aachen

Report Nr.:A 3026/B2 dated 14. 06. 1996, IBAC Aachen

Report Nr.:P 3132-1 dated 27. 08. 2003, Polymer Institute

This system is registered as product a system according to ZTV-ING part 3, section 4



## Product Data

### Form

<b>Appearance / Colours</b>	Clear Glaze:	clear liquid
	Top Coat:	can be supplied in almost any colour shade
<b>Packaging</b>	Clear Glaze:	20 kg pail
	Top Coat:	30 kg pails

### Storage

<b>Storage Conditions / Shelf-Life</b>	36 months from date of production if stored properly in undamaged and unopened original sealed packaging in cool and dry conditions. Protect from direct sunlight and frost.
--	--

### Technical Data

<b>Chemical Base</b>	Acrylate resin in solvent
<b>Density</b>	Clear Glaze: ~ 0.9 kg/l (at +20°C)
	Top Coat: ~ 1.4 kg/l (at +20°C) Dependent on colour shade, small variations are possible.
<b>Solid Volume</b>	Top Coat: ~ 45%
<b>Flash Point</b>	Clear Glaze: +25°C
	Top Coat: +30°C
<b>Layer Thickness</b>	Minimum required dry thickness to achieve full durability characteristics (CO <sub>2</sub> diffusion, adhesion after thermal cycling, etc.) = 101 microns. Maximum required thickness not to go beyond the H <sub>2</sub> O equivalent air thickness of 5 m = 290 microns.

### Carbon Dioxide Diffusion Coefficient (μCO<sub>2</sub>)

Dry film thickness	d = 130 μm
Equivalent air layer thickness	S <sub>D</sub> , CO <sub>2</sub> = 429 m
Diffusion coefficient CO <sub>2</sub>	μCO <sub>2</sub> = 3.3 x 10 <sup>6</sup>
Requirements for protection	S <sub>D</sub> CO <sub>2</sub> ≥ 50 m

### Water Vapour Diffusion Coefficient (μH<sub>2</sub>O)

Dry film thickness	d = 140 μm
Equivalent air layer thickness	S <sub>D</sub> , H <sub>2</sub> O = 2.4 m
Diffusion coefficient H <sub>2</sub> O	μH <sub>2</sub> O = 1.8 x 10 <sup>4</sup>
Requirements for breathability	S <sub>D</sub> , H <sub>2</sub> O ≤ 5 m

## System Information

<b>System Structure</b>	<i>Sikagard®-680 S Clear Glaze:</i>
	As protection and enhancement of exposed aggregate concrete: 2 x Sikagard®-680 S Clear Glaze
	<i>Sikagard®-680 S Top Coat:</i>
	In normal situation: 2 x Sikagard®-680 S Top Coat
	When using bright yellow and red colour shades: 3 x Sikagard®-680 S Top coat
	When combined with hydrophobic impregnation priming coats: 1 - 2 x Sikagard®-740 W or Sikagard®-700 S 2 x Sikagard®-680 S Top Coat

## Application Details

### Consumption

Approx. consumption per application kg/m<sup>2</sup> per coat

Product	Per coat
Sikagard®-680 S Clear Glaze	~ 0.15 kg/m <sup>2</sup>
Sikagard®-680 S Top Coat	~ 0.20 kg/m <sup>2</sup>

### Substrate Preparation

#### Exposed concrete without existing coating:

The surface must be dry, sound and free from loose and friable particles. Suitable preparation methods are steam cleaning, high pressure water jetting or blastcleaning.

New concrete must be at least 28 days old.

(e.g Sika Monotop 620 Sikagard®-720 EpoCem® etc.) can be used – refer to the respective product data sheet. Allow a curing time of at least 4 days before coating (except when the EpoCem is used, then coating can be applied within 24 hours).

#### Exposed concrete with existing coating:

Existing coatings must be tested to confirm their adhesion to the substrate - adhesion test average > 1.0 N/mm<sup>2</sup> with no single value below 0.7 N/mm<sup>2</sup>. – refer to the relevant Method Statement for more details or BS EN 1504 -2

#### Inadequate adhesion:

Existing coatings must be completely removed by suitable methods and the substrate must be sufficiently sound and suitable to be coated as above.

#### Adequate adhesion:

Thorough cleaning of all surfaces by means of steam cleaning or high pressure water jetting. Normally, Sikagard®-680 S can be applied on existing coating without any priming - It is recommended to carry out adhesion testing on a small scale prior to full scale operations.

Note: Existing water-based coating, even well adhering, must be removed completely prior to apply Sikagard®-680 S

### Application Conditions / Limitations

Substrate Temperature	+5°C min. / +35°C max.
Ambient Temperature	+5°C min. / +35°C max.
Relative Air Humidity	< 85%
Dew Point	Temperature must be at least 3°C above dew point

### Application Instructions

Mixing	Sikagard®-680 S is supplied ready for use. Stir thoroughly prior to application.
Application Method / Tools	<p>On very absorbent and/or porous substrate, it is recommended to add about 50% of Sikagard®-680 S Clear Glaze to the first coat of Sikagard®-680 S Top Coat in order to strengthen the substrate and to reduce the risk of a patchy appearance.</p> <p>Sikagard®-680 S (Clear Glaze and Top Coat) can be applied by brush or short-piled lambskin roller.</p> <p>The top coat can also be applied by airless spray: Spray pressure 150 bars, nozzle bore 0.38 - 0.66 mm, spray angle 50 - 80°.</p>
Cleaning of Tools	Clean all tools and application equipment with Sika Thinner C immediately after use. Hardened / cured material can only be removed mechanically.

Waiting Time / Overcoating	Waiting time between coats:	
	Substrate temperature	Time
	+10°C	8 hours
	+20°C	5 hours
	+30°C	3 hours
Note: Refresher coats of Sikagard®-680 S can be applied without priming if the existing coating has been thoroughly cleaned.		
Notes on Application / Limitations	Do not apply when there is:	
	- Expected rain	
	- Relative humidity > 85%	
	- Temperature below +5°C and/or below dew point	
	For lightweight concrete façade, we recommend a crack bridging intermediate coat such as Sikagard®-550 W Elastic.	
	In marine environments or if the concrete surface is exposed to splashes of de-icing salts, an impregnation of Sikagard®- 740W or Sikagard-700 S is recommended as water repellent primer.	
	On fair faced and precast concrete without adequate pore filler (e.g. Sika® MonoTop®- 620 or Sikagard® -720 EpoCem®, bubbles may occur if the application is carried out during rising temperatures.	
	The system is fully resistant for all normal atmospheric exposures and rainfall etc.	
	Splashed water containing de-icing salts or sea water may cause a loss of gloss and colour shade variation. However the protective performances are not adversely affected.	
Curing Details		
Curing Treatment	Sikagard®-680 S does not require any special curing but must be protected from rain for at least 1 hour at +20°C (dust dry in 30 minutes at +20°C).	
Applied Product ready for use	Full cure: ~ 5 days at +20°C	
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.	
Local Restrictions	Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.	
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.	
Legal Notes	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.	

## CE Labelling

The harmonised European standard EN 1504-2 "Products and systems for the protection and repair of concrete structures – Definitions, requirements, quality control and evaluation of conformity – Part 2 Surface protection system for concrete" specifies the requirements for coatings to be used to protect concrete structures (either building or civil engineering structures).

Coatings used as concrete protection fall under this specifications – they need to be CE-labelled as per Annex Za, table Za.1d & 1e, conformity 2+ and 3 and fulfil the requirements of the given mandate of the Construction Product Directives (89/106/EC).

CE	
0921	
Sika Deutschland GmbH Factory Number 2017 Kornwestheimer Straße 103-107 70439 Stuttgart, Germany 08	
0921-CPD-2017 EN 1504-2 Surface protection products Protective coating	
Permeability to CO <sub>2</sub>	S <sub>D</sub> > 50 m
Permeability to water vapour	S <sub>D</sub> < 5 m (class I)
Capillary absorption and permeability to water	$\omega < 0,1 \text{ kg/m}^2 \cdot \text{h}^{0,5}$
Adhesion Strength by pull-off test	$\geq 1,0 \text{ (0,8) N/mm}^2$
Reaction to fire after application	Class E
Dangerous substances comply with 5.3	

## EU Regulation 2004/42

### VOC - Decopaint Directive

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / i type **sb**) is 600 (Limit 2010) for the ready to use product.

The maximum content of **Sikagard®-680 S** is < 500 g/l VOC for the ready to use product.



#### SIKA LIMITED

Head Office · Watchmead · Welwyn Garden City ·  
Hertfordshire · AL7 1BQ · United Kingdom  
Phone: +44 1 707 394444 · Fax: +44 1 707 329129 · [www.sika.co.uk](http://www.sika.co.uk)

